



## DGN FASER PRIVATE LIMITED

R.S. No. 565, Surendranagar – Lakhtar Highway, Near Dedadra Patiya, Surendranagar – 363030 (Guj.)

Phone : 02752-283383, E mail: [dgnfaser@gmail.com](mailto:dgnfaser@gmail.com)

---

Accredited with QMS 9001-2015, EMS 14001-2015 & OH & SAS 18001-2015

### Technical Data Sheet

|                                  |   |                                      |
|----------------------------------|---|--------------------------------------|
| 1. <b>Product</b>                | : | Ceramic Fiber Blanket, Grade: 1430°C |
| 2. <b>Size</b>                   | : | 7.62m X 0.610m X 25mm Thickness,     |
| 3. <b>Density</b>                | : | 128 Kg/m <sup>3</sup> (-10%, + 30%)  |
| 4. <b>Dimensional</b>            | : |                                      |
| Length (mtr.)                    | : | 7.62    (-0, excess is permitted)    |
| Width (mtr.)                     | : | 0.610   (-2%, +10%)                  |
| Thick (mm)                       | : | 25      (-6mm, +19mm)                |
| 5. <b>Shot Content</b>           | : | 30% max.                             |
| 6. <b>Tensile Strength</b>       | : | 40 kPa                               |
| 7. <b>Linear Shrinkage</b>       | : | 4.0% max                             |
| (at 1400°C for 24 Hours)         |   |                                      |
| 8. <b>Fiber Diameter</b>         | : | 2.0 to 4.0 micron                    |
| 9. <b>Thermal Conductivity</b>   | : |                                      |
| (at Mean Temperature 500°C)      |   | 0.150 W/mk                           |
| (at Mean Temperature 300°C)      |   | 0.081 W/mk                           |
| 10. <b>Chemical Composition</b>  | : |                                      |
| Al <sub>2</sub> O <sub>3</sub> % | : | 29 – 37                              |
| SiO <sub>2</sub> %               | : | 42 – 57                              |
| ZrO <sub>2</sub> %               | : | 13 – 18                              |

Material will be as per ASTM C 892 / IS: 15402 Specification